

On the size of linear superpositions in molecular nanomagnets

F. Troiani

S3 Istituto Nanoscienze-CNR, Modena, Italy

P. Zanardi

*Department of Physics and Astronomy, and Center for Quantum Information Science & Technology,
University of Southern California, Los Angeles, CA 90089-0484 and*

Centre for Quantum Technologies, National University of Singapore, 2 Science Drive 3, Singapore 117542

(Dated: April 30, 2013)

Molecular nanomagnets are relatively complex spin systems that exhibit quantum mechanical behavior at low temperatures. Exploiting quantum-information theoretic measures we quantify the size of linear superpositions that can be generated within the ground multiplet of high-spin nanomagnets. In particular, we consider the prototypical single-molecule magnets (namely Mn_{12} and Fe_8) and a physically significant class of spin rings (including Mn_6), all characterized by a ferrimagnetic spin ordering in the ground state. These cases are compared with those achievable in ferromagnetic spin clusters. We show that the size of these linear superpositions can be further enhanced by increasing the asymmetry between the sublattices, and by reducing the competition between exchange interactions within the nanomagnets.

PACS numbers: 03.65.Ta, 75.50.Xx

Molecular nanomagnets provide prototypical examples of zero-dimensional spin systems, with physical properties that can be widely tuned by chemical synthesis [1]. Antiferromagnetic exchange interactions typically result in the presence of different forms of quantum entanglement at low temperatures, such as those between individual spins of a single cluster [2] or the collective spins of weakly coupled molecules [3]. Quite generally, the interest in molecular nanomagnets was aroused by the early observation of quantum effects. These include quantum tunneling of the molecule spin, resulting in a speed-up of the magnetization relaxation [4, 5], and quantum phase interference [6]. More recently, microwave-induced quantum coherences [7, 8] and oscillations [9, 10] were observed in a wide class of spin clusters. These experiments demonstrate the possibility of manipulating the molecule spin state on time scales shorter than the decoherence time, which represents a preliminary requirement for the implementation of quantum-information processing [11, 12].

In all these cases, the relevant quantum coherences are those between states with different spin projection, belonging to the ground S multiplet of the molecular nanomagnet. These linear superpositions can be particularly meaningful in high-spin molecules, also referred to as *single-molecule magnets*. Here, the ground S multiplet may include classical-like states that are mesoscopically different from one another, and whose linear superpositions can thus be regarded as mesoscopic Schrödinger cat states [13]. Hereafter we quantitatively investigate the size of such linear superpositions, starting from realistic spin Hamiltonian models of the nanomagnets. We specifically refer to the most celebrated single-molecule magnets, $[\text{Mn}_{12}\text{O}_{12}(\text{CH}_3\text{COO})_{16}(\text{H}_2\text{O})_4]$ [14] and $[\text{Fe}_8\text{O}_2(\text{OH})_{12}(\text{tacn})_6]\text{Br}_8(\text{H}_2\text{O})_9$ (tacn=1,4,7-triazacyclononane) [15], and to a class of spin rings whose prototype is represented by the $[\text{Mn}(\text{hfac})_2(\text{NITPh})]_6$ molecule (Mn_6) [16]. In all the three molecules (hereafter referred to as Mn_{12} , Fe_8 , and Mn_6) the ground

state is characterized by a ferrimagnetic ordering, with the total spin S resulting from the inequivalence of the two sublattices [1]. The size of possible linear superpositions generated within the ground multiplet is favored by the absence in Mn_6 of competing interactions within each sublattice, and by the large unbalance between their partial spin sums. In Mn_{12} and Fe_8 , the more complex pattern of partially competing exchange interactions limits the classical-like character of the ground states, and thus the measure of the linear superpositions that takes this aspect into account.

The problem of quantifying the size of a linear superposition has been addressed from different perspectives, in order to assess the actual macroscopicity of quantum coherences in infinite physical systems [17–22]. There, the question whether or not a linear superposition is macroscopic is answered by considering the limit of different measures as the number N of the microscopic subsystems tends to infinity. In the present paper, we use two of such measures to quantify the size of linear superpositions in zero-dimensional spin systems. The first measure is based on the quantum Fisher information [19], and quantifies both the non-classicality of the linear superposition $|\Psi\rangle = (|\Psi_1\rangle + |\Psi_2\rangle)/\sqrt{2}$ and the classical-like character of its components in terms of the respective quantum fluctuations of single-spin operators. As showed in following, the advantage of such measure in the present context is at least twofold. Firstly, it quantifies the distinguishability between the two superposed states by means of a physically intuitive quantity, such as the spin projection of the constituent ions. Secondly, it can be expressed in terms of spin-pair correlation functions, that are now experimentally accessible in molecular spin clusters [23]. The second measure we consider quantifies the size of a linear superposition in terms of the possibility to distinguish between the two components $|\Psi_1\rangle$ and $|\Psi_2\rangle$ by means of local measurements. The size of $|\Psi\rangle$ is thus identified with the number of subsystems into which the spin cluster can be partitioned, such that the




FIG. 1: (color online) (a) Spin cluster corresponding to the Fe_8 molecule. The eight $s = 5/2$ spins are divided into the two sublattices A (light and dark blue) and B (red), defined by their relative orientation in the system ground state. Equivalent spins are denoted by the same color. Same line style corresponds to identical values of the exchange coupling between neighboring spin pairs. (b) Spin cluster corresponding to the Mn_{12} molecule, where $s_i^A = 2$ and $s_j^B = 3/2$, with the same conventions as above. (c) Schematics of the double-well potential induced by the crystal field within the ground $S = 10$ multiplet of the two spin clusters, and corresponding level scheme.

which-component information is available in each of the subsystems [24]. The notion of distinguishability can be itself translated in terms of measurement outcomes, but in a way that makes it of no experimental relevance in the present context. In fact, the projective measurement of the individual spins (or of arbitrary subsets of them) that would be required to estimate the distinguishability are presently unfeasible in molecular nanomagnets. On the other hand, this measure has the advantage of being independent on the specific class of one-body operators that we use with the Fisher information, and is thus suitable for comparing the size of linear superpositions obtained in completely different systems.

The paper is organized as follows. In Section I we introduce the measures that are used to quantify the size of the linear superpositions. In Section II we present the results obtained for the Mn_{12} and the Fe_8 spin clusters. In Section III we discuss the case of spin rings, including the Mn_6 molecule. Section IV and V are devoted to a comparison with other molecular spin clusters and to the conclusions, respectively. Finally, in Appendix A we prove the optimality of the staggered magnetization as a one-spin operator for the Fisher information.

I. SIZE OF LINEAR SUPERPOSITIONS IN SPIN CLUSTERS

We consider linear superpositions of the form

$$|\Psi\rangle = \frac{1}{\sqrt{2}}(|\Psi_1\rangle + |\Psi_2\rangle), \quad (1)$$

where $|\Psi_1\rangle$ and $|\Psi_2\rangle$ are two eigenstates of the spin Hamiltonian H_0 of the molecular nanomagnet, that commutes with the total-spin projection S_z . More specifically, we focus on the case where the dominant terms of H_0 are represented by the exchange couplings between the N spins of the cluster, and the states $|\Psi_1\rangle$ and $|\Psi_2\rangle$ belong to the ground S -multiplet, with different values of S_z (M_1 and M_2 , respectively).

A. Quantum Fisher information

The first criterion we use for quantifying the size of the linear superposition is based on the quantum Fisher information [19]. For pure states, such quantity coincides, up to a multiplicative constant, with the variance of the relevant operator X :

$$\mathcal{F}_\Psi(X) = 4[\langle X^2 \rangle - \langle X \rangle^2]. \quad (2)$$

The one-particle operator X that maximizes $\mathcal{F}_\Psi$ should coincide with the one that is best suited to distinguish between the two components. The operator X is thus expected to have largely different expectation values for $|\Psi_1\rangle$ and $|\Psi_2\rangle$, and small fluctuations within each component. In the class of systems considered hereafter, this criterion is fully met by the staggered magnetization operator S_z^* :

$$X = S_z^* = S_z^A - S_z^B = \sum_{k=1}^{N_A} s_{k,z}^A - \sum_{l=1}^{N_B} s_{l,z}^B, \quad (3)$$

where A and B are two sublattices into which the spin cluster is partitioned ($N_A + N_B = N$). For each system considered hereafter, each sublattice is defined so as to include all the spins s_i with the same sign of the expectation value $\langle \Psi_k | s_{z,i} | \Psi_k \rangle$, for any given component $k = 1, 2$ of the linear superposition. The staggered magnetization S_z^* maximizes the Fisher information for the most relevant linear superpositions of the form Eq. 1 (namely, those between components with large values of $|M_1 - M_2|$), within the class of operators $X = \sum_{i=1}^N \hat{\mathbf{n}}_i \cdot \mathbf{s}_i$ (with $\hat{\mathbf{n}}_i^2 = 1$) (see Appendix A). Such linear combinations of single-spin terms have an intuitive physical meaning and represent the most significant operators from an experimental viewpoint, for their variance can be decomposed into experimentally accessible quantities, such as spin-pair correlation functions [23]. Quadratic functions of $s_{i,\alpha}$ (with $\alpha = x, y, z$), are instead unsuitable for characterizing the above linear superpositions, for they give identical expectation values for pairs of states that are the time-reversal of one another. Cubic (or higher) powers of the single-spin operators don't correspond to any




FIG. 2: (color online) (a) Effective size $D_{FI}(\Psi)$ of the linear superpositions $|\Psi\rangle$ formed by the ground states of the Mn_{12} molecule with total spin projections M_1 and M_2 . The maximum possible value for the spin cluster is $\sum_i s_i = 22$. In the cases $M_1 = M_2$ we set $D_{FI} = 0$. (b) Size of the same linear superpositions based on the relative Fisher information, $D_{RFI}(\Psi)$.

observable quantity in molecular nanomagnets, and even less do their fluctuations [1].

For a given spin cluster, the maximum of the Fisher information corresponding to the staggered magnetization is given by:

$$\mathcal{F}_{max} = 4 \left(\sum_{\chi=A,B} \sum_{i=1}^{N_\chi} \|s_{i,z}^\chi\| \right)^2 = 4 \left(\sum_{\chi=A,B} \sum_{i=1}^{N_\chi} s_i^\chi \right)^2, \quad (4)$$

where the norm of the spin operator is here defined as its largest eigenvalue (in modulus). This value corresponds to the state $|\Psi_{max}\rangle = (|\Psi_1^{max}\rangle + |\Psi_2^{max}\rangle)/\sqrt{2}$, where the components are given by

$$|\Psi_{k=1,2}^{max}\rangle = \otimes_{i=1}^{N_A} |m_{i,k}^A = \pm s_i^A\rangle \otimes_{j=1}^{N_B} |m_{j,k}^B = \mp s_j^B\rangle. \quad (5)$$

As discussed below, these states can also be regarded as the most classical-like states of the spin cluster, and have vanishing fluctuations of the staggered magnetization operator.

The quantum Fisher information can be used to define the effective size of the linear superposition, along the lines of Ref. [19]:

$$D_{FI}(\Psi) = \frac{\mathcal{F}_\Psi(S_z^*)}{4 \sum_{\chi=A,B} \sum_{i=1}^{N_\chi} s_i^\chi}. \quad (6)$$

Such quantity can take any value in the interval $[0, \sum_{\chi=A,B} \sum_{i=1}^{N_\chi} s_i^\chi]$. The maximum size of a linear superposition that can in principle be generated in a given spin cluster thus depends not only on the number N of the constituent spins, but also on their values s_i . This follows from the use of spin operators - rather than generic norm-one operators - in the quantum Fisher information. It also assigns a larger size to the linear superposition of the states $|\Psi_{k=1,2}^{max}\rangle$, with respect to, e.g., one where the components are given by the product of single-spin states $|m_{i,k}^\chi\rangle$ ($\chi = A, B$) with non-maximal spin projections ($|m_{i,k}^\chi| \neq s_i^\chi$). We note that such discriminations also allows to link the present measure $D_{FI}(\Psi)$ to the ones that quantify the size of a linear superposition in

terms of its decoherence rate [20]. In fact, the fragility of a linear superposition between two eigenstates of a molecular spin cluster was shown to depend on their distinguishability in terms of single-spin expectation values [25], and is thus an increasing function of the quantities $|\langle \Psi_1 | S_z^* | \Psi_1 \rangle - \langle \Psi_2 | S_z^* | \Psi_2 \rangle|$.

The absolute value of the Fisher information characterizes the linear superposition in terms of the quantum fluctuations of the operator S_z^* . However, it doesn't discriminate between the contribution to such fluctuations coming from the components $|\Psi_1\rangle$ and $|\Psi_2\rangle$, and the one that results from their linear superposition. In the spirit of the Schrödinger gedanken experiment [13], the superposed states should in fact approach a classical character, and therefore present the smallest amount of quantum fluctuations allowed by the uncertainty relations. In this perspective, a suitable figure of merit for the linear superposition is represented by the relative Fisher information, where the variance of the relevant operator in $|\Psi\rangle$ is normalized to that in the components [19]:

$$D_{RFI}(\Psi) = \frac{\mathcal{F}_\Psi(S_z^*)}{\frac{1}{2} [\mathcal{F}_{\Psi_1}(S_z^*) + \mathcal{F}_{\Psi_2}(S_z^*)]}. \quad (7)$$

For a spin cluster, the nonclassicality of a state can in general be traced back to the presence of entanglement between the spins and of quantum fluctuations in the single-spin operators. A classical-like $|\Psi_k\rangle$ can thus be identified with the product of single-spin coherent states $|\phi\rangle$, defined by the relation $|\langle \phi | s | \phi \rangle| = s$ [26]. In the present case, the only relevant coherent states are represented by $|m = \pm s\rangle$, due to symmetry reasons. In fact, being the two components of Eq. 1 eigenstates of S_z , the single-spin reduced density matrix is given by

$$\rho_{i,k}^{(1)} = \text{tr}_{j \neq i} \{ |\Psi_k\rangle \langle \Psi_k| \} = \sum_{m_i} p_k(m_i) |m_i\rangle \langle m_i|, \quad (8)$$

and the in-plane components of the spin have vanishing expectation values: $\langle \Psi_k | s_{i,x} | \Psi_k \rangle = \langle \Psi_k | s_{i,y} | \Psi_k \rangle = 0$. The classical-like character of the states $|\Psi_k\rangle$ is thus quantified globally by the fluctuations in the staggered magnetization ($\mathcal{F}_{\Psi_k}(S_z^*)$), and, at the single-spin level, by the von Neumann entropies $S(s_i, k) = -\sum_{m_i} p_k(m_i) \ln[p_k(m_i)]$ or by the populations $p_k(m_i = \pm s_i)$. In order to maximize the above sizes of the linear superposition $|\Psi\rangle$, the components should approach the form $|\Psi_k^{max}\rangle$ (Eq. 4), characterized by $\mathcal{F}_{\Psi_k}(S_z^*) = S(s_i, k) = 0$, and $p_k(m_i = \pm s_i) = 1$.

We finally note that general symmetry arguments allow to simplify the calculation of the above quantities. In the relevant case where the two components are the time reversal of one another ($M_1 = -M_2$), the following relations apply:

$$\langle \Psi_1 | S_z^* | \Psi_1 \rangle = -\langle \Psi_2 | S_z^* | \Psi_2 \rangle, \quad \langle \Psi | S_z^* | \Psi \rangle = 0 \quad (9)$$

$$\langle \Psi_k | (S_z^*)^2 | \Psi_k \rangle = \langle \Psi | (S_z^*)^2 | \Psi \rangle. \quad (10)$$

The expression of the relative Fisher information thus simplifies to:

$$D_{RFI}(\Psi) = \frac{\langle \Psi_1 | (S_z^*)^2 | \Psi_1 \rangle}{\langle \Psi_1 | (S_z^*)^2 | \Psi_1 \rangle - \langle \Psi_1 | S_z^* | \Psi_1 \rangle^2}. \quad (11)$$




FIG. 3: (color online) Probability $P_l^{(q)}$ of discriminating between the two components $|\Psi_1\rangle$ and $|\Psi_2\rangle$ ($M_1 = -M_2 = M$) of the Mn_{12} spin cluster. The probabilities refer to subensembles formed by q spins: blue, green and red squares correspond to the spins s_1^A , s_2^A and s_1^B , respectively ($q = 1$); the purple squares correspond to the pair formed by the spins s_1^A and s_1^B ($q = 2$). Inset: Values of the von Neumann entropy $S(s_i^X, k)$ for the three inequivalent spins corresponding to each component $|\Psi_k\rangle$. Same convention as above for the colors.

More generally, the values of the Fisher information corresponding to different linear superpositions of the above type (Eq. 1) are not independent from one another. In fact, the operators S_z^* and $(S_z^*)^2$ can be written as components of irreducible tensor operators, whose expectation values within a given S -multiplet are related by the Wigner-Eckart theorem [27]. In particular, $S_z^* = S_{q=0}^{(p=1)}$ is the component $q = 0$ of a tensor with rank $p = 1$, whereas $(S_z^*)^2 = -S_0^{(0)}/\sqrt{3} + S_0^{(2)}\sqrt{2}/\sqrt{3}$ can be written as the sum of a scalar and of the 0-th component of a tensor with $p = 2$. As far as S_z^* is concerned, the Wigner-Eckart theorem thus implies:

$$\langle \alpha S M | S_z^* | \alpha S M \rangle = \langle \alpha S | S_0^{(1)} | \alpha S \rangle A_{M0M}^{S1S}, \quad (12)$$

where $A_{m_1 m_2 m}^{j_1 j_2 j}$ are the Clebsch-Gordan coefficients and α denotes the ground S -multiplet of the spin Hamiltonian. The expectation values of $(S_z^*)^2$ obey instead the equation:

$$\begin{aligned} \langle \alpha S M | (S_z^*)^2 | \alpha S M \rangle = & -\langle \alpha S | S_0^{(0)} | \alpha S \rangle / \sqrt{3} \\ & + \langle \alpha S | S_0^{(2)} | \alpha S \rangle A_{M0M}^{S2S} \sqrt{2} / \sqrt{3}. \end{aligned} \quad (13)$$

In the following, it will thus be sufficient to compute the values of S_z^* and $(S_z^*)^2$ for one and two different values of M , respectively, in order to derive all the others from the reduced matrix elements. The same applies to the single- and two-spin expectation values discussed throughout the paper.

B. Distinguishability by local measurements

The effective size of the linear superposition $|\Psi\rangle$ can also be quantified in terms of the maximal number of

subsystems that allow to distinguish between $|\Psi_1\rangle$ and $|\Psi_2\rangle$ with probability higher than $1 - \delta$ [24]. The maximum probability of successfully discriminating the two states by performing an optimal measurement on q spins of the cluster is given by:

$$P_l^{(q)} = \frac{1}{2} + \frac{1}{4} \|\rho_{l,1}^{(q)} - \rho_{l,2}^{(q)}\|_1, \quad (14)$$

where $\rho_{l,k}^{(q)}$ is the reduced density matrix of the l -th subsystem formed by q spins, obtained from the state $|\Psi_k\rangle$; $\|X\|_1 := \sum_i |\lambda_i|$ (with λ_i the eigenvalues of X) is the trace norm. For the N -spin clusters considered hereafter, the effective dimension based on the distinguishability of the two components by means of local measurements is given by:

$$D_{LM}(\Psi, \delta) = \max_{\{A_l\}} n, \quad (15)$$

where n is the number of subsystems A_l into which the spin cluster is partitioned, and the maximization is performed over all the partitions such that $P_l > 1 - \delta$ for all $l = 1, \dots, n$, with $\bigcup_{l=1}^n A_l = \mathcal{S}$ and $\mathcal{S}$ the N -spin system.

The size quantification based on the local distinguishability has the advantage, with respect to the previously defined measure, of being independent on the specific class of operators X . It thus allows to compare the sizes of linear superpositions obtained in different systems. On the other hand, the connection to quantities that are experimentally accessible in molecular nanomagnets is not straightforward. The maximum probability $P_l^{(q)}$ is obtained by a projective measurement in the basis that diagonalizes $\rho_{l,1}^{(q)} - \rho_{l,2}^{(q)}$ (see Ref. [24] and references therein). In the case where the subsystem A_l is represented by a single spin s_i , given the form of the reduced density matrix (Eq. 8), the optimum measurement is that of $s_{z,i}$. In the case where A_l includes more than one spin, the expression of the relevant observable cannot be determined a priori, and might be a non-trivial function of the spin operators. In any case, projective measurements of single spins, or of specific subsystems of the spin cluster, are presently unavailable in molecular magnetism.

II. SINGLE-MOLECULE MAGNETS

The prototypical high-spin molecules are probably represented by Mn_{12} and Fe_8 [1]. Hereafter we compute the size of the linear superpositions that can be obtained by linearly combining eigenstates of their spin Hamiltonian belonging to the ground S multiplet.

The dominant part H_{Exc} of the spin Hamiltonian of both these molecules corresponds to the isotropic exchange interaction between neighboring spins. Therefore, the total spin S can be regarded as a good quantum number. Smaller terms, such as those related to crystal field, can be treated at a perturbative level and projected within the ground S -multiplet [1]. In particular, the crystal field anisotropy is often assumed to be quadratic in the total spin operators, and its main term reflects an




FIG. 4: (color online) Effective size $D_{FI}(\Psi)$ of the linear superposition $|\Psi\rangle$, with $M_1 = +M$ and $M_2 = -M$, for the Fe_8 spin cluster: the black squares are the computed values, the red curve corresponds to the exponential fit. Inset: Same function computed for each of the two components $|\Psi_k\rangle$. The white squares and the green curve correspond to the computed values and to the exponential fit, respectively.

axial symmetry: $H_{ACF} = DS_z^2$ (with $D < 0$), where z is the principal symmetry axis of the molecule. This removes the degeneracy within the ground S multiplet of H_{Exc} , giving rise to the characteristic double-well potential, with the two degenerate ground states $M = \pm S$ (Fig. 1(c)). Hereafter we consider linear superpositions of the eigenstates of $H_0 = H_{Exc} + H_{ACF}$. These can be induced by static terms that don't commute with S_z , such as the rhombic crystal field $H_{RCF} = E(S_x^2 - S_y^2)$, or a transverse magnetic field. Alternatively, arbitrary linear superpositions can be generated by multifrequency pulse sequences, that exploit the removed degeneracy between the different $\Delta M = \pm 1$ transitions [11].

A. The Mn_{12} molecule

The Mn_{12} molecule represents the first and prototypical example of a single-molecule magnet. It essentially consists of an external ring, formed by eight Mn^{3+} ions (each carrying an $s = 2$ spin), and an internal tetrahedron, formed by four Mn^{4+} ions (with $s = 3/2$). Experimental investigation combined with spin Hamiltonian calculations allow to group the spins in two sublattices, depending on their relative orientation. The sublattices, labeled A and B , are formed by the external and internal spins, respectively (Fig. 1(b)). The dominant part H_{Exc} of the spin Hamiltonian includes the exchange interactions between neighboring spins belonging to the same sublattice (H_A and H_B) or to different ones (H_{AB}):

$$H_A = J_A \sum_{i=1}^8 \mathbf{s}_i^A \cdot \mathbf{s}_{i+1}^A, \quad H_B = J_B \sum_{i=1}^4 \sum_{j=1}^{i-1} \mathbf{s}_i^B \cdot \mathbf{s}_j^B$$

$$H_{AB} = J_{AB} \sum_{i=1}^4 \mathbf{s}_{2i-1}^A \cdot \mathbf{s}_i^B + J'_{AB} \sum_{i=1}^4 \mathbf{s}_{2i}^A \cdot (\mathbf{s}_i^B + \mathbf{s}_{i+1}^B) \quad (16)$$

where $s_i^A = 2$, $s_j^B = 3/2$, $\mathbf{s}_9^A \equiv \mathbf{s}_1^A$, and $\mathbf{s}_5^B \equiv \mathbf{s}_1^B$. The calculations presented hereafter are obtained by setting [28]: $J_A = -64.5 \text{ K}$, $J_B = 85 \text{ K}$, $J_{AB} = 215 \text{ K}$, $J'_{AB} = 85 \text{ K}$. The ground-state multiplet of $H_{Exc} = H_A + H_B + H_{AB}$ belongs to the $S = 10$ subspace.

Before discussing the size of the linear superpositions $|\Psi\rangle$, we characterize the eigenstates of H_{Exc} in terms of single-spin states and staggered magnetization, in order to verify their resemblance to a classical-like spin state. The maximally polarized states ($M_1 = 10$) present the highest degree of polarization on the external spins s_i^A , and more specifically on the even-numbered ones [28]. This is reflected by the main populations in the reduced density matrices $\rho_{i,k}^{(1)}$, which correspond for all spins to the states with $|m_i| = s_i$, with $p_1(m_1^A = 2) = 0.692$, $p_1(m_2^A = 2) = 0.845$, and $p_1(m_1^B = -3/2) = 0.591$. The main configuration of the $M_1 = 10$ eigenstate is represented by the classical-like ground state, with $|\langle \Psi_1 = 10 | \Psi_1^{max} \rangle| = 0.307$. The expectation value of the staggered magnetization and its variance are given by 17.6 (out of a maximum of $\sum_{\chi=A,B} \sum_i s_i^\chi = 22$) and 7.00, respectively. These values undergo respectively a linear decrease and an exponential increase with M_1 , that reflects the dependence on the total-spin projection of the relevant Clebsch-Gordan coefficients (see Eqs. 12 and 13).

The size of the linear superpositions between the ground states of H_{Exc} is first quantified in terms of the quantum Fisher information. The dependence of the size $D_{FI}(\Psi)$ on the total spin projections M_1 and M_2 of the components $|\Psi_k\rangle$ is reported in Fig. 2(a). As expectable, the maximum of $D_{FI}(\Psi)$ is achieved for the maximally polarized components ($M_1 = -M_2 = 10$). The size of the linear superposition shows a strong dependence on $|M_1 - M_2|$, while it depends only weakly on $|M_1 + M_2|$. At a qualitative level, the same features characterize the relative Fisher information, and the corresponding size $D_{RFI}(\Psi)$ (Fig. 2(b)). From a quantitative point of view, we note that the maximum value of both the absolute and the relative Fisher information is comparable to that obtained for Fe_8 (see the following Subsection, and Table I), in spite of the fact that the sum of the spins gives a slightly smaller value in the latter case.

The size of the linear superposition $|\Psi\rangle$ can also be quantified in terms of the distinguishability by means of local measurements of the two components. The probability $P_l^{(1)}$ of discriminating between $|\Psi_1\rangle$ and $|\Psi_2\rangle$ with single-spin measurements is reported in Fig. 3 for the three inequivalent spins, as a function of $M_1 = -M_2 = M$. On average, the probabilities are slightly lower than those obtained for the Fe_8 cluster (see below). In particular, we find that only one of the spins (s_2^A , green squares) reaches values of $P_l^{(1)} > 0.99$, and only for $M = 10$. In order to estimate the effective size D_{LM} for such case, we need to consider different partitions of the spin cluster, where the spins with least distinguishable states are grouped together in larger subsystems A_l , so as to achieve values of the probability $P_l^{(q)}$ above the threshold. The partition with the largest number of subsystems that fulfils such requirement is defined by the four subsystems

$A_l = \{s_{2l-1}^A, s_l^B\}$ (purple squares), with $1 \leq l \leq 4$, and by other four, each formed by an individual spin: $A_{l+4} = \{s_{2l}^A\}$. As a result, $D_{LM}(\Psi, \delta = 10^{-2}) = 8$ for $M = 10$.

B. The Fe₈ molecule

The second most investigated single-molecule magnet is commonly indicated as Fe₈. The magnetic core of Fe₈ consists of eight Fe³⁺ ions, each carrying an $s = 5/2$ spin (Fig. 1(a)). Experimental evidence exists that the Fe₈ molecule has a ground $S = 10$ multiplet, resulting from a ferrimagnetic ordering of the spins [1]. The spin-Hamiltonian calculations allow to further specify the spin ordering. This is characterized by six spins (sublattice A , blue circles) oriented parallel to each other and to the total spin, while the remaining two (sublattice B , red circles) are oriented in the opposite direction. The dominant part of the spin Hamiltonian includes the exchange couplings represented in the Fig. 1(a), and is given by $H_{Exc} = H_A + H_{AB}$, where:

$$H_A = J_A \sum_{i=1}^2 s_{4+i}^A \cdot (s_{2i-1}^A + s_{2i}^A) + J'_A s_5^A \cdot s_6^A, \quad (17)$$

$$H_{AB} = J_{AB} \sum_{i=5}^6 \sum_{j=1}^2 s_i^A \cdot s_j^B + J'_{AB} [s_2^B \cdot (s_2^A + s_3^A) + s_1^B \cdot (s_1^A + s_4^A)], \quad (18)$$

with $s_i^A = s_j^B = 5/2$. A good agreement with the experimental data is obtained with the following set of values for the exchange constants: $J_A = 26$ K, $J'_A = 36$ K, $J_{AB} = 200$ K, $J'_{AB} = 59$ K [28]. Even in the absence of a magnetic field, the degeneracy in the ground S multiplet is removed by the crystal field. In particular, due to the relatively high $|D/E|$ ratio, the two lowest states in the double well are approximately degenerate and with defined values of the total-spin projection, while a certain degree of admixture is induced in the low- $|M|$ states by the rhombic term. Hereafter, the two components of the linear superposition are identified with the eigenstates of $H_0 = H_{Exc} + H_{ACF}$ (i.e. the part of H that commutes with S_z), that can be coherently coupled by the rhombic term H_{RCF} .

We start by verifying to which extent the eigenstates of H_0 approach the classical-like form $|\Psi_k^{max}\rangle$ (Eq. 5). The single-spin states corresponding to the maximally polarized eigenstates $M_1 = 10$ are characterized themselves by a strong degree of polarization, where the largest populations correspond to the states with the largest spin projection: $p_1(m_1^A = 5/2) = 0.976$, $p_1(m_2^A = 5/2) = 0.668$, and $p_1(m_1^B = -5/2) = 0.643$. Remarkable differences emerge in this respect between the four external spins ($\chi = A, 1 \leq i \leq 4$) and the four central ones. The resulting overlap between the $M_1 = 10$ ground state and the main spin configuration is given by $|\langle \Psi_1 | \Psi_1^{max} \rangle| = 0.687$, while $|\langle \Psi_1 | S_z^* | \Psi_1 \rangle| = 28.0$. States with a lower M_1 are characterized by less defined single-spin states, and by a larger fluctuations of the staggered magnetization S_z^* ,




FIG. 5: (color online) Probability $P_l^{(q)}$ of discriminating between the two components $|\Psi_1\rangle$ and $|\Psi_2\rangle$ (with $M_1 = +M$ and $M_2 = -M$) of the Fe₈ spin cluster. The probabilities refer to subensembles formed by q spins: red, blue and green squares correspond to the spins s_5^A , s_6^A and s_1^A , respectively ($q = 1$); the purple squares correspond to the four central spins s_5^A , s_6^A , s_1^A and s_2^A ($q = 4$). Inset: Values of the von Neumann entropy $S(s_i^x, k)$ for the three inequivalent spins corresponding to each component $|\Psi_k\rangle$. Same convention as above for the colors.

that decreases exponentially with the total-spin projection (see the insets of Figs. 4 and 5, respectively).

We next quantify the size of the linear superpositions between states with opposite spin projections: $M_1 = -M_2 = M > 0$. The two components of such linear superpositions are increasingly distinguishable in terms of S_z^* for increasing values of M , being also $\langle M_1 | S_z^* | M_1 \rangle - \langle M_2 | S_z^* | M_2 \rangle \propto M$. Therefore, the fluctuations of the staggered magnetization in $|\Psi\rangle$ grow exponentially with M , and so does the effective size $D_{FI}(\Psi)$ of the linear superposition (Fig. 4). Such exponential increase $e^{\alpha M}$, with $\alpha \simeq 0.178$, is independent on the specific form of the eigenstates, for it reflects the exponential increase with M of the Clebsch-Gordan coefficients $A_{MOM}^{S_z^* S}$ (see Eq. 13). For $M = 10$, $D_{FI}(\Psi)$ approaches the maximum possible value for this system, $\sum_{\chi=A,B} \sum_i s_i^x = 20$. The same exponential increase characterizes the dependence on M of the relative Fisher information $D_{RFI}(\Psi)$ (not shown), that ranges from 1.148 to 48.707, for $1 \leq M \leq 10$.

We next consider the size of the linear superpositions based on the distinguishability of the two components $|\Psi_1\rangle$ and $|\Psi_2\rangle$ by means of optimized local measurements. The corresponding size of the linear superposition is given by the quantity $D_{LM}(\Psi, \delta)$ (Eq. 15), here with δ to 10^{-2} . The dependence of $D_{LM}(\Psi)$ on M is reported in Fig. 5 for each of the three inequivalent spins in the cluster. As suggested by the expectation values of the above comments on the single-spin states, $P_l^{(1)}$ is highest for the external spins belonging to the sublattice A ($1 \leq i \leq 4$, green squares), and lies above the threshold $1 - \delta$ for $M \geq 9$. The probabilities corresponding to the central spins (red and blue squares) lie

instead below the threshold for all the considered cases. In order to efficiently discriminate between the two components $|\Psi_k\rangle$, one needs to perform an ideal measurement on the whole central core of the cluster, i.e. on the spin subensemble A_5 formed by s_1^B , s_2^B , s_5^A , and s_6^A (purple squares). Here, the condition $P_5^{(4)} > 0.99$ is achieved for $M \geq 9$. We note that such condition cannot be fulfilled by further partitioning the subensemble corresponding to the four central spins, for all the three inequivalent pairs give $P_l^{(2)} < 0.99$ ($l = 1, 2, 3$) for any M (not shown). From the above results, one can conclude that $D_{LM}(\Psi, \delta = 10^{-2}) = 5$ for $M = 9$ and $M = 10$, where the optimum partition corresponds to $A_l = \{s_l^A\}$ ($l = 1, \dots, 4$) and $A_5 = \{s_1^B, s_2^B, s_5^A, s_6^A\}$. Therefore, while the larger number of spins doesn't result in a larger size $D_{FI}(\Psi)$ for Mn_{12} with respect to Fe_8 , it does allow to obtain larger linear superpositions in terms of $D_{LM}(\Psi, \delta)$.

III. BIPARTITE SPIN RINGS

The Mn_{12} and Fe_8 molecules are relatively complex spin clusters, where the polarization of the spins is to some extent limited by the competition between different exchange paths. This limits the size of the linear superpositions that can be possibly generated in these systems, both in terms of Fisher information of the staggered magnetization and of distinguishability of the two components by means of local measurements. Heterometallic spin rings formed by alternate sequences of inequivalent spins represent a class of simple spin clusters, that are immune to such limitations. The spins s_A and $s_B < s_A$ belonging to the two sublattices, with $N_A = N_B = N/2$, are coupled to each other by isotropic exchange interaction between nearest neighbors:

$$H = J_{AB} \sum_{i=1}^{N/2} \mathbf{s}_i^A \cdot (\mathbf{s}_i^B + \mathbf{s}_{i+1}^B), \quad (19)$$

where $\mathbf{s}_{N/2+1}^B \equiv \mathbf{s}_1^B$. The antiferromagnetic coupling ($J_{AB} > 0$), combined with the spin difference $s_A - s_B$, results in the formation of an $S = N(s_A - s_B)/2$ ground multiplet. A prototypical example of such a spin cluster is represented by the Mn_6 ring, formed by six Mn^{2+} ions ($s_A = 5/2$) coupled to six organic radicals ($s_B = 1/2$). In order to highlight the role played by the inequivalence between the two spins, this case will be contrasted with that of analogous spin rings, characterized by $N_A = N_B = 6$, $s_B = 1/2$ and $s_A = 1, 3/2, 2$. We shall focus on the most relevant linear superposition, namely that between the $M_1 = +S$ and $M_2 = -S$ eigenstates of the ground S -multiplet.

The dependence of $D_{FI}(\Psi)$ on the value of s_A is reported in Fig. 6(a). The calculated values (black squares) follow a linear dependence (red line) on s_A . For increasing s_A , the value of $D_{FI}(\Psi)$ approaches its maximum possible value $6(s_A + s_B)$ (white squares). We also note that the size of the linear superposition corresponding to the Mn_6 molecule has approximately the




FIG. 6: (color online) (a) Effective size of the linear superposition of the maximally polarized ground states ($M = \pm 6(s_A - s_B)$) of the bipartite rings, as a function of s_A ($s_B = 1/2$). The values of $D_{FI}(\Psi)$ (black squares) displays a linear dependence on s_B (red line). The maximum values corresponding to the four cases are given by the white squares. (b) Size of the same linear superpositions quantified by $D_{RFI}(\Psi)$. The red curve represents an exponential fit of the computed points.

same value than that obtained for the Fe_8 and Mn_{12} spin clusters (Table I). If normalized to the theoretical maximum ($\sum_{\chi=A,B} \sum_{i=1}^{N_\chi} s_i^\chi = 18$), such value is the highest amongst the considered molecules. The effective size based on the relative Fisher information grows exponentially with s_A (Fig. 6(b)), and reaches for the Mn_6 molecule a value which is much larger than that of the previously considered molecules (Table I). This results from the classical-like character of the $M_1 = 12$ states ($|\Psi_1|\Psi_1^{max}\rangle| = 0.762$), corresponding to small values of the fluctuations in staggered magnetization and to strongly polarized single-spin states: $p_1(m_1^A = 5/2) = 0.915$ and $p_1(m_1^B = -1/2) = 0.911$. As discussed in the following Section, the size of the linear superpositions could be further increased if the parallel alignment were not only allowed by the absence of antiferromagnetic couplings within each sublattice, but favored by the presence of strong ferromagnetic interactions.

We finally consider the size of linear superposition between the ground states with $M_1 = -M_2 = 12$ of the Mn_6 ring, based on the distinguishability of the components by local measurements. This is given by $D_{LM}(\Psi, \delta = 10^{-2}) = 7$. In fact, the two components can be efficiently distinguished by single-spin measurements performed on the spins of sublattice A . Instead, a probability above the threshold $1 - \delta$ cannot be achieved with any three spins s_i^B , nor with smaller subensembles. Therefore, the partition of the spin cluster into seven subsystems - six including one spin of A each ($A_l = \{s_l^A\}$, with $l = 1, \dots, 6$), one including all the spins of B ($A_7 = \{s_1^B, s_2^B, s_3^B, s_4^B, s_5^B, s_6^B\}$) is the optimum one.

IV. COMPARISON WITH OTHER SPIN CLUSTERS

The molecular nanomagnets considered so far, Mn_{12} , Fe_8 , and Mn_6 , can be regarded as three representative examples of high-spin molecules, with ground states that are suitable for generating linear superpositions of relatively large sizes. It might be useful, however, to highlight how such sizes can be further increased, for example

by engineering the exchange couplings, without modifying the geometry of the spin cluster. In particular, one can consider the case where the dominant part of the spin Hamiltonian is still represented by isotropic exchange, and the linear superpositions involve the two states with $M_1 = +S$ and $M_2 = -S$. Also, the sublattices A and B for each of the spin clusters are left unchanged with respect to those represented in Fig. 1. We find that the states that maximize the fluctuations of the staggered magnetization are the ones with maximum values of the partial spin sums, and with $\mathbf{S}_A$ and $\mathbf{S}_B$ antiparallel to each other:

$$|\Phi_{k=1,2}\rangle = |S_A=S_A^{max}, S_B=S_B^{max}, M=\pm(S_A-S_B)\rangle, \quad (20)$$

where $S_{\chi=A,B}^{max} = \sum_{i=1}^{N_\chi} s_i^\chi$ [29]. These states correspond to the maximally polarized ground states of H_{Exc} , in the limit of strong ferromagnetic intra-lattice couplings, and weak antiferromagnetic inter-lattice interactions: $J_A, J_B < 0$, $J_{AB} > 0$, and $|J_A|, |J_B| \gg J_{AB}$. Besides, $|\Phi_{k=1,2}\rangle$ approach the classical-like states $|\Psi_k^{max}\rangle$ (Eq. 5) for increasing values of the difference $S_A - S_B$. In Table I we report the sizes of the linear superpositions between the eigenstates $M_1 = S$ and $M_2 = -S$ for the three spin clusters Mn_{12} , Fe_8 , and Mn_6 , along with those of the corresponding linear superpositions $(|\Phi_1\rangle + |\Phi_2\rangle)/\sqrt{2}$. These latter values (in parentheses) approach the maximum possible values that could be obtained within the same spin clusters, corresponding to the states $|\Psi_{max}\rangle$.

Molecular spin clusters with only ferromagnetic interactions can be regarded as the limiting cases of the ones considered so far, with $N_A = N$ and $N_B = 0$. Here, the ground states corresponding to $M = \pm S$, with $S = \sum_{i=1}^N s_i$, correspond exactly to classical-like states of the form $|\Psi_k^{max}\rangle$. The sizes of the largest linear superposition between $M = +S$ and $M = -S$ are given simply by $D_{FI}(\Psi) = S$ and $D_{LM}(\Psi, \delta) = N$, where the latter expression is independent on δ . As a remarkable example of such a molecular nanomagnet, we mention $[\text{Et}_3\text{NH}]_2[\text{Mn}(\text{CH}_3\text{CN})_4(\text{H}_2\text{O})_2][\text{Mn}_{10}\text{O}_4(\text{biphen})_4\text{Br}_{12}]$, Mn_{10} in short [30]. Such a spin cluster has an $S = 23$ ground multiplet, and allows in principle to generate larger linear superpositions, with respect to the previously considered molecules (Table I). On the other hand, we note that the cost of a linear superposition (e.g., in terms of the number of microwave pulses) tends to increase with the difference between the total spin projections, $M_1 - M_2$. Therefore, molecular spin clusters with a ferrimagnetic ground state can in principle allow to generate larger linear superpositions with respect to ferromagnetic ones, for a given S . For example, the values of $D_{FI}(\Psi)$ and $D_{LM}(\Psi)$ obtained for Fe_8 (Table I) are larger than the ones that could be obtained within a cluster of $N = 4$ ferromagnetically coupled $s = 5/2$ spins: $D_{FI}(\Psi) = 10$ and $D_{LM}(\Psi)4$.

Molecular spin clusters can also exhibit mesoscopic quantum coherence in the form of Néel-vector tunneling. Prototypical systems where such phenomenon has been investigated are even-numbered spin rings, with antiferromagnetic exchange between nearest neighbors [31–34]. Here, the sublattices A and B have equal sizes, and

	Mn_{12}	Fe_8	Mn_6	Mn_{10}
$D_{FI}(\Psi)$	14.4 (21.0)	16.5 (18.3)	16.0 (17.1)	23.0 (23.0)
$D_{FI}(\Psi_k)$	0.318 (0.140)	0.339 (0.121)	0.115 (0.0584)	0.0 (0.0)
$D_{RFI}(\Psi)$	45.4 (143)	48.7 (152)	139 (293)	– –
$D_{LM}(\Psi, \delta = 10^{-2})$	8 (10)	5 (8)	7 (8)	10 (10)

TABLE I: Size of the linear superposition $|\Psi\rangle$ between the maximally polarized ground states of the considered molecules: Mn_{12} , Fe_8 , Mn_6 , Mn_{10} . The values in parentheses refer to the models of the spin clusters where the two macrospins $S_A = \sum_{i=1}^{N_A} s_i^A$ and $S_B = \sum_{i=1}^{N_B} s_i^B$ are antiferromagnetically coupled. The values of $D_{FI}(\Psi)$ corresponding to the states $|\Psi_{max}\rangle$ of Mn_{12} , Fe_8 , Mn_6 and Mn_{10} are 22, 20, 18, and 23, respectively.

are formed by the odd- and even-numbered spins, respectively. In the simplest case, the easy-axis anisotropy tends to enhance in the ground state $|\Psi\rangle$ the weight of the classical-like ground states $|\Psi_{k=1,2}^{max}\rangle$, while quantum tunneling between them is induced by an in-plane magnetic field. We note however that the application of the measures $D_{RFI}(\Psi)$ and $D_{LM}(\Psi)$ to such states is not straightforward. In fact, the overlap between the actual ground state $|\Psi\rangle$ and $|\Psi_{max}\rangle$ is only moderate for realistic values of the physical parameters, and doesn't allow to unambiguously decompose $|\Psi\rangle$ into a linear superposition of two components (Eq. 1). On the other hand, the fluctuations of the staggered magnetization alone (and thus $D_{FI}(\Psi)$) don't allow to distinguish between a mesoscopic Schrödinger cat state and one which is quantum-mechanical in a broader sense [19].

V. CONCLUSIONS

In conclusion, resorting to different quantum-information theoretic measures we have quantitatively investigated the size of linear superpositions that can be generated in molecular nanomagnets. The prototypical single-molecule magnets, namely Mn_{12} and Fe_8 , exhibit comparable values of the considered measures. Linear superpositions of larger sizes can be possibly generated in the ring-shaped molecule Mn_6 , at least in terms of the relative Fisher information. The absence of competing interactions within each of the two sublattices (A and B) and a large unbalance between the partial spin sums (S_A and S_B) are identified as rule-of-thumb principles for maximizing the size of linear superpositions within the ground S multiplet and for a given geometry. While these criteria are fully met by spin clusters with ferromagnetic exchange only, ferrimagnetic systems might allow a good compromise between large sizes of the linear superpositions and moderate values of the total-spin projection difference $M_1 - M_2$.

Acknowledgements

This work has been financially supported by the FIRB project RBFR12RPD1 of the Italian MIUR, by the ARO MURI grant W911NF-11-1-0268, and by NSF grant numbers PHY-969969 and PHY-803304. Useful input from J.I. Cirac is gratefully acknowledged.

Appendix A: Maximization of the quantum Fisher information

Hereafter, we maximize the quantum Fisher information $\mathcal{F}_\psi(X)$ as a function of the operator X , where X is a linear combination of single-spin operators:

$$X = \sum_{i=1}^N x_i = \sum_{i=1}^N \hat{\mathbf{n}}_i \cdot \mathbf{s}_i, \quad (\text{A1})$$

with $\hat{\mathbf{n}} = (n_x, n_y, n_z)$ and $\hat{\mathbf{n}}^2 = 1$. The maximization is performed for the most relevant linear superpositions considered above, namely those where $|\Psi_1\rangle$ and $|\Psi_2\rangle$ have opposite values of the total-spin projection ($M_1 = -M_2 \equiv M > 0$).

We start by considering the case where the versors $\hat{\mathbf{n}}_i$ are all identical: $X = \hat{\mathbf{n}} \cdot \sum_{i=1}^N \mathbf{s}_i = \hat{\mathbf{n}} \cdot \mathbf{S}$. Being the two components the time-reversal of one another, the following relations apply:

$$\langle \Psi_1 | X | \Psi_1 \rangle = -\langle \Psi_2 | X | \Psi_2 \rangle = n_z M, \quad \langle \Psi | X | \Psi \rangle = 0, \quad (\text{A2})$$

$$\langle \Psi_1 | X^2 | \Psi_1 \rangle = \langle \Psi_2 | X^2 | \Psi_2 \rangle = \langle \Psi | X^2 | \Psi \rangle = n_z^2 M^2. \quad (\text{A3})$$

In Eq. A3, we have made use of the assumption that $M_1 - M_2 > 2$, which allows to neglect the contribution to the variance of X coming from the coherence between the two components: $\langle \Psi_1 | X^2 | \Psi_2 \rangle = 0$. As a result, the Fisher information of the state $|\Psi\rangle$ reads:

$$\mathcal{F}_\psi(X) = 2[S(S+1) - M^2] + 2n_z^2[3M^2 - S(S+1)]. \quad (\text{A4})$$

Here, the equivalence between the x and y directions allows to set, without loss of generality, $n_y = 0$ and thus $n_x^2 = 1 - n_z^2$. From the above equation it follows that $\mathcal{F}_\psi(X)$ is maximized by the operator

$$\begin{aligned} X &= S_z \text{ for } M^2 > S(S+1)/3, \\ X &= S_x \text{ for } M^2 < S(S+1)/3. \end{aligned} \quad (\text{A5})$$

In the case of the previously considered molecules, the ground multiplets correspond to $S = 10$ (Mn_{12} and Fe_8) and $S = 12$ (Mn_6). These values lead to the conditions $M \geq 7$ and $M \geq 8$, respectively, for having $X = S_z$ as an optimal total-spin component. For smaller values of M , the component with the largest fluctuations in $|\Psi\rangle$ is no longer S_z , but S_x . We note, however, that such fluctuations don't qualify the corresponding linear superpositions as good examples of mesoscopic linear superpositions, for $n_z = 0$ also maximizes the fluctuations at the level of the single component. In fact, the variance of X corresponding to $|\Psi_1\rangle$ is given by the following equation:

$$\mathcal{V}_{\Psi_1}(X) = (1 - n_z^2)[S(S+1) - M^2]/2, \quad (\text{A6})$$

which monotonically decreases with n_z^2 . For linear superpositions between strongly polarized states ($M^2 > S(S+1)/3$), the operator $X = S_z$ thus maximizes both the absolute and the relative Fisher information of $|\Psi\rangle$.

We next consider a more general class of operators X , by admitting different versors $\hat{\mathbf{n}}_i$, while keeping the condition $M_1 - M_2 = 2M_1 > 2$. The Fisher information of the state $|\Psi\rangle$ reads:

$$\begin{aligned} \mathcal{F}_\psi(X) &= 4 \sum_{i,j=1}^N \{ (n_{i,x}n_{j,x} + n_{i,y}n_{j,y}) \langle \Psi_1 | s_{i,x}s_{j,x} | \Psi_1 \rangle \\ &\quad + n_{i,z}n_{j,z} \langle \Psi_1 | s_{i,z}s_{j,z} | \Psi_1 \rangle \} \equiv \sum_{i,j=1}^N F_{ij}(X, \Psi), \end{aligned} \quad (\text{A7})$$

where we have made use of the relations in Eq. A2. The operator X that maximizes such quantity is defined by the optimal values of the versor components $n_{i,\alpha}$ ($\alpha = x, y, z$), and depends on the values of the two-spin correlation functions that characterize the system eigenstates $|\Psi_k\rangle$. Such problem is in fact equivalent to computing the ground state of a system formed by N classical spins $\hat{\mathbf{n}}_i$, interacting through anisotropic exchange couplings $J_{ij}^\perp = \langle \Psi_1 | s_{i,x}s_{j,x} | \Psi_1 \rangle$ and $J_{ij}^\parallel = \langle \Psi_1 | s_{i,z}s_{j,z} | \Psi_1 \rangle$. As long as the highly polarized components $|\Psi_k\rangle$ are concerned, there is no competition between the maximization of each contribution $F_{ij}(X)$. In fact, all the versors tend to be aligned along z , being

$$|\langle \Psi_1 | s_{i,x}s_{j,x} | \Psi_1 \rangle| < |\langle \Psi_1 | s_{i,z}s_{j,z} | \Psi_1 \rangle| \quad (\text{A8})$$

for all $1 \leq i, j \leq N$. Besides, the N spins can be divided into two sublattices A and B such that $\langle \Psi_1 | s_{i,z}s_{j,z} | \Psi_1 \rangle$ is positive for all pairs of spins belonging to the same sublattice and negative for all pairs where the two spins belong to different sublattices. The ground state of the classical spin system thus simply corresponds to $n_{z,i} = +1$ for all $s_i \in A$, and $n_{z,i} = -1$ for all $s_i \in B$. This set of versors also defines the optimum operator X . We have numerically checked that the above conditions for the spin-pair correlation functions are fulfilled by the considered molecules for large enough values of M . In particular, the inequalities coincide with those obtained above in the case of identical versors: $M \geq 7$ for Fe_8 and Mn_{12} , $M \geq 8$ for Mn_6 . We note that the sublattices A and B that are defined on the basis of the correlation functions $\langle \Psi_1 | s_{i,z}s_{j,z} | \Psi_1 \rangle$ coincide with those introduced on the basis of the single-spin expectation values (see Fig. 1).

As a final remark, we note that any operator X which is quadratic in the single-spin operators, such as $X = \sum_{i,j=1}^N (\hat{\mathbf{n}}_{ij} \cdot \mathbf{s}_i)(\hat{\mathbf{n}}'_{ij} \cdot \mathbf{s}_j)$, has identical variance for the state $|\Psi\rangle$ and for the two components $|\Psi_k\rangle$, provided that these are sufficiently polarized ($M_1 - M_2 > 4$, implies in fact that the coherence doesn't provide any contribution to the expectation value of X^2). Therefore, the only fluctuations that are captured by $\mathcal{F}_\psi(X)$ are the ones that are independent on the linear superposition, and the relative Fisher information is always 1. This makes the above quadratic operator X unsuitable for quantifying the size of the linear superpositions $|\Psi\rangle$.

-
- [1] D. Gatteschi, R. Sessoli, and J. Villain, *Molecular nano-magnets* (Oxford University Press, 1992).
- [2] I. Siloi and F. Troiani, Phys. Rev. B **86**, 224404 (2012).
- [3] A. Candini, G. Lorusso, F. Troiani, A. Ghirri, S. Carretta, P. Santini, G. Amoretti, C. Muryn, F. Tuna, G. Timco, et al., Phys. Rev. Lett. **104**, 037203 (2010).
- [4] L. Thomas, F. Lioni, R. Ballou, D. Gatteschi, R. Sessoli, and B. Barbara, Nature **383**, 145 (1996).
- [5] J. R. Friedman, M. P. Sarachik, J. Tejada, and R. Ziolo, Phys. Rev. Lett. **76**, 3830 (1996).
- [6] W. Wernsdorfer and R. Sessoli, **284**, 133 (1999).
- [7] A. Ardavan, O. Rival, J. J. L. Morton, S. J. Blundell, A. M. Tyryshkin, G. A. Timco, and R. E. P. Winpenny, Phys. Rev. Lett. **98**, 057201 (2007).
- [8] S. Takahashi, J. van Tol, C. C. Beedle, D. N. Hendrickson, L.-C. Brunel, and M. S. Sherwin, Phys. Rev. Lett. **102**, 087603 (2009).
- [9] S. Bertaina, S. Gambarelli, T. Mitra, B. Tsukerblat, A. Müller, and B. Barbara, Nature **453**, 203 (2008).
- [10] C. Schlegel, J. van Slageren, M. Manoli, E. K. Brechin, and M. Dressel, Phys. Rev. Lett. **101**, 147203 (2008).
- [11] M. Leuenberger and D. Loss, Nature **410**, 789 (2001).
- [12] F. Troiani, M. Affronte, S. Carretta, P. Santini, and G. Amoretti, Phys. Rev. Lett. **94**, 190501 (2005).
- [13] E. Schrödinger, Naturwiss. **23**, 807 (1935).
- [14] T. Lis, Acta Crystallog. B **36**, 2042 (1980).
- [15] K. Wieghardt, K. Pohl, I. Jibril, and G. Huttner, **23**, 77 (1984).
- [16] A. Caneschi, D. Gatteschi, J. Laugier, P. Rey, R. Sessoli, and C. Zanchini, J. Am. Phys. Soc. **110**, 2795 (1998).
- [17] A. J. Leggett, Prog. Theor. Phys. Suppl. **69**, 80 (1980).
- [18] G. Björk and P. G. L. Mana, J. Opt. B: Quantum Semiclass. Opt. **6**, 429 (2004).
- [19] F. Fröwis and W. Dür, New Journal of Physics **14**, 093039 (2012).
- [20] W. Dür, C. Simon, and J. I. Cirac, Phys. Rev. Lett. **89**, 210402 (2002).
- [21] A. Shimizu and T. Miyadera, Phys. Rev. Lett. **89**, 270403 (2002).
- [22] F. Marquardt, B. Abel, and J. von Delft, Phys. Rev. A **78**, 012109 (2008).
- [23] M. L. Baker, T. Guidi, S. Carretta, J. Ollivier, H. Mutka, H. U. Güdel, G. A. Timco, E. J. L. McInnes, G. Amoretti, R. E. P. Winpenny, et al., Nat. Phys. **8**, 906 (2012).
- [24] J. I. Korsbakken, K. B. Whaley, J. Dubois, and J. I. Cirac, Phys. Rev. A **75**, 042106 (2007).
- [25] F. Troiani, D. Stepanenko, and D. Loss, Phys. Rev. B **86**, 161409 (2012).
- [26] A. Auerbach, *Interacting electrons and quantum magnetism* (Springer, 1994).
- [27] M. Tinkham, *Group theory and quantum mechanics* (McGraw-Hill, 2007).
- [28] C. Raghu, I. Rudra, D. Sen, and S. Ramasesha, Phys. Rev. B **64**, 064419 (2001).
- [29] For each value of S and M , we block diagonalize the operator $K = (S_z^A - S_z^B)^2 = -M^2 + 2[(S_z^A)^2 + (S_z^B)^2]$. Each block corresponds to defined values of the partial spin sums S_A and S_B , given that $[K, \mathbf{S}_A^2] = [K, \mathbf{S}_B^2] = 0$. For the considered spin clusters, the largest eigenvalue of K always corresponds to $S_A = S_A^{max}$ and $S_B = S_B^{max}$.
- [30] A. Caneschi, D. Gatteschi, R. Sessoli, and J. Schweizer, Physica B **241**, 600 (1997).
- [31] A. Chioleri and D. Loss, Phys. Rev. Lett. **80**, 169 (1998).
- [32] P. Santini, S. Carretta, G. Amoretti, T. Guidi, R. Caciuffo, A. Caneschi, D. Rovai, Y. Qiu, and J. R. D. Copley, Phys. Rev. B **71**, 184405 (2005).
- [33] O. Waldmann, T. C. Stamatatos, G. Christou, H. U. Güdel, I. Sheikin, and H. Mutka, Phys. Rev. Lett. **102**, 157202 (2009).
- [34] F. Meier and D. Loss, Phys. Rev. Lett. **86**, 5373 (2001).